

Product name	Product group	Production location
Blenheim Red Multi	D1	Hedikhuizen

The raw materials are excavated in Weichsel loam layers, the local loam of Aeolian origin dating from the Ice Age. This löss mainly consists of a silt-like fraction, suited ideally for the manufacturing of hand form bricks. By using specific sand types for surface covering, the desired colour is achieved.

Colour						
Red brown facing brick with dark shades						
Format						
Moulding me	Noulding method Hand form					
DF: 215 x 103 x 66 mm	Between bate	atches the average size and color may slightly differ.				
Essential Ch	aracteristics - EN	EN771-1				
C E EN 771-1 - 0620-CPR-9788	0	UK CA EN 771 - 1855-CPR-24912				
2+		2+				
Dimensional tolerances	T2					
Range	R1					
Active Soluble Salts	S2					
Mean Compressive strength	>= 10 N/mr	mm² Tested to the bed face				
Normalized Compressive strength	>= 10 N/mr	mm² Tested to the bed face				
Dimensional stability	NPD					
Bond Strength general	0,15 N/mm	nm²				
Bond Strength thin layer	0,30 N/mm	nm²				
Reaction to fire	A1	Category				
Water absorption	<= 15% m/r	/md				
Water vapour permeability	5/10					
Net dry density	1800 kg/m³ (³ (D1)				
Gross dry density	1780 kg/m³ (³ (D1)				
Thermal conductivity Lambda 50/50	<=0,49 W/n	/m.K				
Durability against freeze thaw	F2					
Dangerous substances	NL-BSB	B According to Annex ZA 3				
Other Characteristics						
Initial rate of water absorption - Non-coated Bricks	1,5 - 4,0 kg/m ² (IW3)	m ² .min Value according EN771-1:2011 - 5.3.8				

Other Characteristics						
Initial rate of water absorption - Non-coated Bricks	1,5 - 4,0 kg/m².min (IW3)	Value according EN771-1:2011 - 5.3.8				
Initial rate of water absorption - Coated bricks	0,5 - 1,5 kg/m².min (IW2)	Value according EN771-1:2011 - 5.3.8				
Freeze/thaw resistance - PTV 23-002	NPD	NBN 27-009				
Thermal conductivity Lambda 90/90	NPD					
Thermal conductivity Lambda Ui	NPD					
Thermal conductivity Lambda Ue	NPD					









Cutting



Sto	rage	& h	andling

Cutting with power tools may generate dust. This dust may contain silica or quartz particulate which may constitute a hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3).

Store packs on a clean surface and cover them
Process from multiple packs at the same time
Follow the Vandersanden processing guidelines

^{*}All our Coated bricks are only coated on the facing sides. Coated products are specially labeled and recognisable with a "C" logo on the top left-hand side of the packaging. Always check if using coated or non-coated bricks. Match the mortar to the specified initial water absorption.