

Authorised signatories:

L Cooney ( \* )

W Leighton ( )

S Connor ( )




## CERTIFICATE OF TEST

### PARTICLE SIZE DISTRIBUTION REPORT SUMMARY

|                 |                                       |                  |                  |
|-----------------|---------------------------------------|------------------|------------------|
| LABORATORY REF: | G4414                                 | SITE/CLIENT REF: | GALLAGHER QUARRY |
| SCHEME/SITE:    | GALLAGHER AGGREGATES - QUARRY TESTING |                  |                  |
| MATERIAL DESC:  | 0-6mm Crushed Rock Fines              |                  |                  |
| MATERIAL SPEC:  |                                       |                  |                  |
| SAMPLE TYPE     | Bulk                                  | Material Type:   | CRF              |
| SOURCE          | Hermitage Quarry                      | Ticket No.       | N/A              |
| DATE SAMPLED    | 11/07/2023                            | Date Received    | 12/07/2023       |
| SAMPLED BY      | LD                                    | Date Tested      | 13/07/2023       |

| Sieve (mm) | Passing % | Specification |
|------------|-----------|---------------|
| 125        | 100       | N/A           |
| 63         | 100       |               |
| 31.5       | 100       |               |
| 20         | 100       |               |
| 16         | 100       |               |
| 14         | 100       |               |
| 10         | 100       |               |
| 8          | 100       |               |
| 6.3        | 98        |               |
| 4          | 81        |               |
| 2.8        | 72        |               |
| 2          | 63        |               |
| 1          | 51        |               |
| 0.5        | 42        |               |
| 0.25       | 32        |               |
| 0.125      | 23        |               |
| 0.063      | 17.7      |               |



Remarks:

#### Certificate of sampling: Not available

Sampling method: BS EN 932-1:1997

Preparation method: BS EN 932-2:1999

Test method: BS EN 933-1:2012

WET ☒ DRY ☐

#### Client Detail

Gallagher Aggregates Limited

Hermitage Quarry, Hermitage Lane,

Barming, Maidstone, Kent ME16 7NS

Name: Lee Cooney

Signed