



Never compromise on quality!

GLASS-MATE MIRROR **ADHESIVE**

Neutral Cure Silicone for Mirrors

Technical Data Sheet



MATE SEALANT & ADHESIVE RANGE

Description:

A low modulus, neutral cure silicone adhesive. Suitable for interior fixing of mirrors, coated glass or metal panels.

Uses

A ready to use, one-part silicone adhesive which is non-corrosive and odourless. GLASS-MATE has excellent unprimed adhesion on most mirror coatings and has outstanding resistance to heat and humidity. It's properties are unaffected by sunlight, ultra-violet radiation and temperature extremes.

Bond It GLASS-MATE is suitable for internal bonding of mirrors, glazed surfaces, ceramics, enamel, metals, PVCu, polycarbonate and treated or untreated wood, to most common substrates.

Preparation

Ensure all surfaces are clean, dry and free from grease or any contaminants that may hinder adhesion.

Application

Apply using a standard sealant gun. Cut tip from cartridge, be careful not to damage the screw thread. Cut off top of nozzle at an angle of approximately 45° to an opening of approximately 10mm. Screw on nozzle and place cartridge in a standard sealant gun.

For glass thickness of 2 to 4mm apply a 10mm bead of adhesive at 100mm intervals vertically to the back of the mirror, or surface to be bonded. Place the mirror in position and apply even pressure. Provide temporary support (tape) whilst the adhesive cures. The edges of the mirror can also be sealed with GLASS-MATE if required but leave 24 hours after fixing.


For glass thicknesses above 6mm, mirrors greater than 1m² area or mirrors on ceilings or sloping walls, GLASS-MATE MUST be used in conjunction with mechanical fixings.

Note: this product is not suitable for use as a sole fixing for safety backed mirrors.

Tools can be cleaned with WHITE SPIRIT or Bond It MULTI-WIPES prior to curing taking place.

Limitations

This product should not be used in the manufacture of structural glazing. It is also not



suitable for aquarium assembly or for jointing in swimming pools

ALWAYS carry out an adhesion test first.

Container Size

EU3 plastic cartridge.

Colours

Available in translucent only.

Shelf Life

Minimum 12 months from date of manufacture when stored in unopened tubes.

Storage Conditions

Store in cool, dry conditions at a temperature between +5 to +30°C. Protect from frost.

Disposal of Containers

Do not leave empty containers where residue could be harmful to children, animals or the environment. Remove any containers to a central disposal point in accordance with local regulations.

Health & Safety

Please refer to separate material safety data sheet for full handling, use and storage instructions. Keep out of reach of children. It is the users responsibility to determine suitability for use. If in doubt contact our Technical Department for advice.

Note: this information is for general guidance only, since site conditions and labour are beyond our control. It is recommended that users make their own tests to determine suitability.

Specification Summary

| Skinning Time | Less than 30 minutes |
|-------------------------|--|
| Full Cure | 24-48 hours depending on conditions and bead depth |
| Extensibility | Up to 450% at breaking point |
| Application Temperature | e +5 to + 30°C |
| Service Temperature | -40 to + 120°C continuous exposure, higher temperatures can be withstood for limited periods |
| Adhesion | Good to glass, concrete, ceramics, timber, ferrous metals and most building materials |



Product / Order Details:

| Code | Colour | Size | Barcode |
|--------|-------------|------|---------------|
| BDMIRT | Translucent | EU3 | 5060021363695 |







absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies raw materials are also being used. The recommendations do not absolve the user from the obligation of investigating the possibility of infringement of third parties rights and, if necessary clarifying the position. Recommendations for use do not constitute a warranty, either expressed or implied, of the fitness or suitability of the

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not



ISO 45001





Head Office: Unit G16 River Bank Way, Lowfields Business Park, Elland, West Yorkshire HX5 9DN.

Telephone: +44 (0)1422 315300 Fax +44 (0)1422 315310 Email: salesuk@bonditgroup.com Website: www.bonditgroup.com



products for a particular purpose.